

40 C.F.R. § 238.20

Definitions.

For the purpose of this part:

Percent elongation at break means the percent increase in length of the plastic material caused by a tensile load. Percent elongation at break shall be calculated by dividing the extension at the moment of rupture of the specimen by the initial gage length of the specimen and multiplying by 100.

This document is only available to subscribers. Please log in or purchase access.

[Purchase Login](#)